ESD-SAFE SPRAY TRIGGER BOTTLE · ADJUSTABLE NOZZLE

I.C.® ESD SPRAY TRIGGER BOTTLES

Static dissipative blue bottle · Adjustable spray nozzle · Stainless spring-action trigger pump · 16 & 32 oz

PRODUCT DESCRIPTION

I.C. ESD Safe Spray Trigger Bottles are designed to safely dispense most cleaning solutions in any cleanroom or sterile environment. Surface resistivity of 10^9 to 10^{10} Ω/sq and an average static decay rate of 0.5 seconds at 40% RH allow ease of access into static-sensitive environments. An adjustable spray nozzle and stainless-steel spring-action pump provide a constant flow that will not corrode with repeated exposure to most chemicals.

DIRECTIONS FOR USE

Unfasten the pump from the bottle to fill the ESD bottle with solution. Tightly refasten the pump and press to prime the solution.

USES

- For use in a cleanroom or sterile environment
- For use in dispensing cleaning solution or antistatic
- For use in storing cleaning solutions or solvents

APPLICATIONS

Electronics Manufacturing, Cleanrooms, Static-Sensitive Environments.

FEATURES & BENEFITS

FLOW ADJUSTMENT	Adjustable spray nozzle allows for total control of spray pressure
SPRAY TRIGGER CONTROL	Can be pumped partially for control over solution spray
NON-CORRODING	Stainless-steel will not corrode from repeated exposure to chemicals and solvents
FULL-LENGTH STRAW	Straw attachment reaches the corner of the bottle, leaving no solution to waste
LIMITLESS ACCESSIBILITY	Eliminate lab restrictions by placing unsafe materials in ESD-safe containers
HIGH DURABILITY	MDPE is highly durable and chemical resistant
GRIP RIGHT MATERIAL	Flexible material allows for precise and appropriate resistance
LEAK-PROOF	Moldings are fitted to their matching tops and form a seal when enclosed
CLOSE QUARTERS	Material can be kept within reach inside of your workstation
ESD BLUE	Designed retaining the iconic "ESD-Safe" blue tint to be easily identifiable
EASY-SPOT MATERIAL	Translucent material allows for easily identifiable inner contents and levels
SAFER PLASTIC	Made with no PBDE, BPA, or other known plastic contaminants
CONTAMINANT-FREE	Free of amines, amides, and other known antistatic additive contaminants
STAINLESS MATERIAL	Non-stick plastic cleanses all contents and contaminants from its surface
ODOR RESISTANT	Free of trace odors or fragrances left by solvents and other chemicals
DISHWASHER SAFE	Can be washed on the top rack of a dishwasher for cleaning and reuse
ECO-FRIENDLY	Material is formulated to be recyclable and reusable

FREE OF

BPA-FREE	PHTHALATE-FREE
PVC-FREE	PBDE-FREE
CONTAMINANT-FREE	LEAK-FREE
DISHWASHER-SAFE	ECO-SAFE

MATERIAL & ESD DATA

MATERIAL	MDPE with antistatic additive
COLOR	ESD blue, translucent
SURFACE RESISTIVITY	10^9 to 10^{10} Ω/sq
STATIC DECAY	Average 0.5 s at 40% RH
ADDITIVES	Free of amines and amides

WORKPLACE SPECIFICATIONS

- Supports an ANSI/ESD S20.20 program
- Exceeds MIL-B-81705 & NFPA-56A: electrostatic decay in accordance with Federal Test Standard 101, Method 4046
- Tested to ESD ADV 11.21: surface resistance of electrostatically dissipative materials between 1×10^4 and $<1\times10^{11}$
- Meets EIA 625 triboelectric charge standards
- Helps meet ANSI/ESD S4.1
- DOD-HDBK-263 Military Spec Compliant

R&R LOTION USA

I.C.® ESD SPRAY TRIGGER BOTTLES

EFFICACY TESTING

Static decay (5 kV @ 40% humidity) — the ability of a grounded material to dissipate a known charge induced or applied onto its surface.

CUTOFF	MIN	MAX	AVERAGE
1%	0.04 s	0.07 s	0.05 s
10%	0.02 s	0.03 s	0.03 s

Surface resistivity (100 V @ 40% humidity), test method ASTM D257, Ω/sq.

SUBJECT	MIN	MAX	AVERAGE
1%	1.86×10^{10}	2.18×10^{10}	1.97×10^{10}
10%	4.08×10^{10}	5.03×10^{10}	4.48×10^{10}

Surface resistance (100 V @ 40% humidity).

CUTOFF	MIN	MAX	AVERAGE
1%	4.22×10^{8}	7.00×10^{8}	5.51×10^{8}
10%	4.50×10^{7}	1.18×10^{8}	7.02×10^{7}

Static decay, packaging material (decay time in seconds, 5 kV @ 15% RH).

MATERIAL	PVC SLEEVE	PE FOAM	PS FOAM
Result	0.35	0.17	0.17

I.C. ESD bottles solvent residue testing (seven-day exposure). The pH of the water solutions was the same (ca. 5.9) before and after; no color change or other physical change was noted for any of the solvents.

SOLVENT	WT. RESIDUE (G)	CONC. (MG/ML)	CONC. (PPM)
L-TCE	0.0256	0.13	97
L-MEK	0.0191	0.096	120
L-IPA	0.0082	0.041	52
L-H_2O	<0.001	<0.01	<5

CHEMICAL PROPERTIES

I.C. ESD Safe Bottles use MDPE and an antistatic additive which is compliant with FDA regulation for use in food contact: 21 CFR 177.1520 · 21 CFR 178.2010 · 21 CFR 178.3297 · 21 CFR 178.3120. Does not contain BPA, phthalates, or heavy metals.

QUICK CHEMICAL REGULATORY REFERENCES

PROP 65	No known substances
TSCA	No known substances
SARA	No known substances
REACH	No known substances
ROHS	No known substances

SIZES & PART NUMBERS

PART NO.	SIZE	CASE	UPC
SCB-16-ESD	16 oz. spray trigger bottle	10	666080848101
SCB-32-ESD	32 oz. spray trigger bottle	12	666080848095

CHEMICAL COMPATIBILITY & CLEANING

For chemical compatibility or resistance information, refer to the ESD Bottle Chemical Resistance Chart at **rrlotion.com/esd-bottle-chemical-resistance-chart/**. Bottles can be washed on the top rack of a dishwasher for cleaning and reuse.

STORAGE & SHELF LIFE

This product has a shelf life of at least 24 months from the date of manufacture. Some ESD bottles will degrade over time depending on the solvents used and frequency of use.

REGULATORY

This product is an ESD product, manufactured and labeled in compliance with Federal Regulation and current Good Manufacturing Practices (cGMP). R&R Lotion is an FDA and EPA registered and audited facility.

FDA EST. ID	3004167955
EPA FACILITY	91651-AZ-001
FDA DRUG CODE PREFIX	59555

SAFETY DATA SHEETS

For safety, environmental, handling, first aid and disposal information, refer to the Safety Data Sheet (ESD Bottles) in the SDS library at **rrlotion.com/msds/**

QUALITY ASSURANCE

Facility standards. R&R Lotion products are manufactured in facilities which follow Current Good Manufacturing Practice (cGMP) and/or Cosmetic GMP requirements.

Material standards. All raw material used for production undergoes a thorough quality control process before being used for manufacturing.

Equipment standards. All equipment used in manufacturing and production areas is regularly inspected and maintained to ensure consistent and controlled results.

Finished product testing. Each batch produced by R&R Lotion goes through physical and chemical testing before being released for distribution. This involves testing of appearance, color, electrostatic discharge, and density.

R&R LOTION USA

This information and all further technical advice are based upon our present knowledge and experience. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use. The claims made may not have been approved for use in all countries. R&R Lotion Inc assumes no obligation or liability for the information in this document. No warranties are given; all implied warranties of merchantability or fitness for a particular purpose are expressly excluded. Dated: 10/2026 (supersedes TDS dated 08/01/2022).